



DÄMMJUTE

Recycling JUTE insulation boards

Description	Dämmjute
European Technical Assessment	ETA 20/0606
Components	82 – 86 % jute fibers, 11 – 13% bicomponent polyester binding fibres, 3 - 5% soda
Basic Works Requirement 1: Mechanical resistance and stability	
<i>not relevant</i>	
Basic Works Requirement 2: Safety in case of fire	
Reaction to fire (DIN EN 13501-1)	Class E
Basic Works Requirement 3: Hygiene, health and environment	
Biological resistance (growth of mould fungus) <small>(Annex B of EAD 040005-00-1201, EN ISO 846))</small>	Level 0
Basic Works Requirement 4: Safety and accessibility in use	
<i>not relevant</i>	
Basic Works Requirement 5: Protection against noise	
<i>not relevant</i>	
Basic Works Requirement 6: Energy economy and heat retention	
Thermal conductivity λ_D , 23,50 <small>EN ISO 10456, Annex A of EAD 040005-00-1201)</small>	0,0369 [W/m.K]
λ_D , 23,80 for germany	0,039 [W/m.K]
Water vapour diffusion resistance <small>(EN 12086)</small>	≤ 2.4
Water absorption (EN 1609, method A)	$\leq 3 \text{ kg/m}^2$
Geometry	
- width (DIN EN 822)	$\pm 1.5 \%$ T2 (according to EN 13171)
- thickness (DIN EN 823)	No performance assessed
- length	Note: According to EN 13171 there is no upper limit for length of mats
Density (EN 1602)	32 kg/m^3 tolerance: $\pm 15\%$
Dimensional stability under specified and humidity	$\leq 3\%$
Tensile strength parallel to faces (EN 1608)	$\geq 20 \text{ kPa}$

This technical data sheet corresponds to the technical status at the time of publishing and loses its validity when a new edition is published. It is valid in V with other documents from JUTA a.s. Please refer to our processing instructions when processing. The requirements of national building regulations/law must be observed. JUTA a.s. excludes any liability. This also applies to printing or typographical errors and subsequent changes to technical information.